



WWJMRD 2024; 10(03): 82-86

www.wwjmr.com

International Journal

Peer Reviewed Journal

Refereed Journal

Indexed Journal

Impact Factor SJIF 2017:

5.182 2018: 5.51, (ISI) 2020-

2021: 1.361

E-ISSN: 2454-6615

**B. A. Shingade**

Department of Physics,  
Bhawabhuti Mahavidyalaya,  
Amgaon, India.

**R. M. Belekar**

Department of Physics,  
Institute of Science, Nagpuri,  
India.

**A.S. Kakade**

Department of Physics,  
Amolakachand  
Mahavidyalaya, Yawatmal,  
India.

**R.K. Mahadule**

Department of Physics,  
Narayanrao Kale Smurti  
Model College, Karanja,  
Wardha, India.

**V.C. Raghorte**

Department of Physics,  
S.Chandra Mahila  
Mahavidyalaya, Sadak Arjuni  
Gondia, India.

**N.S. Meshram**

Department of Physics, Dr.  
Ambedkar College,  
Deekshabhoomi, Nagpur,  
India.

**Correspondence:**

**B. A. Shingade**

Department of Physics,  
Bhawabhuti Mahavidyalaya,  
Amgaon, India.

## Investigations of Vicker hardness, XRD, FTIR, TGA, EDX Of 0.8% L-Leucine Doped in Ammonium Dihydrogen Phosphate (ADP) Single Crystal

**B. A. Shingade, R. M. Belekar, A.S. Kakade, R.K. Mahadule, V.C. Raghorte, N.S. Meshram**


### Abstract

Ammonium dihydrogen phosphate (ADP) ( $\text{NH}_4\text{H}_2\text{PO}_4$ ) single crystals were grown by slow evaporation method using doped 0.8% L-Leucine. The X-ray diffraction analysis of the as-grown ADP crystals showed that it possesses tetragonal structure having lattice parameters  $a = 7.4854 \text{ \AA}$  and  $c = 7.5377 \text{ \AA}$ . The Fourier transform infrared spectroscopy (FTIR) of as-grown ADP crystal taken between wave-number 400 to 4000  $\text{cm}^{-1}$  showed peaks due to vibration and stretching of functional group O-N=P and  $-\text{ONO}_2$  in 400 to 912.16  $\text{cm}^{-1}$ , P = O and O-H in 1100.50 to 1446.67  $\text{cm}^{-1}$  and O-H and N-H in 2409.81 to 3253.71  $\text{cm}^{-1}$  range. The thermal properties of the as-grown ADP crystals were studied by thermogravimetric analysis (TGA). The thermal activation energy determined from the TGA curve using Broido, Piloyan-Novikova (PN) and Coats Redfern (CR) relations were in good agreement with each other and Energy Dispersive X-Ray Analysis (EDX). The obtained results are discussed in details.

**Keywords:** FTIR, XRD, TGA, EDAX, Vicker Hardness L-Leucine.

### 1. Introduction

Ammonium Dihydrogen Phosphate (ADP) is a representative of hydrogen bonded materials that possesses excellent dielectric, piezoelectric, anti-ferroelectric, electro-optic and nonlinear optical properties. Growth and studies of ammonium dihydrogen phosphate is a centre of attention to researchers because of its unique properties and wide applications. Single crystals of ADP are used for frequency doubling and frequency tripling of laser systems, optical switches in inertial confinement fusion and acoustic-optical Devices [1]. ADP crystallizes in a body centered tetragonal structure with the space group  $I 4 2d$  and has tetra molecular unit cell [2] with unit cell parameters  $a = b = 7.4854 \text{ \AA}$  and  $c = 7.5377 \text{ \AA}$ . ADP has been the subject of a wide variety of investigations over the past decades. Reasonable studies have been done on the growth and properties of pure ADP [3-4]. In recent years, efforts have been taken to improve the quality, growth rate and properties of ADP, by employing new growth techniques, and also by the addition of organic, inorganic and semi organic impurities [5-6]. Organic nonlinear optical materials have large optical susceptibilities, inherent ultrafast response times, and high optical thresholds for laser power as compared with inorganic materials. Amino acids are interesting materials for NLO applications as they contain a proton donor carboxyl acid ( $-\text{COOH}$ ) group and proton acceptor amino ( $-\text{NH}_2$ ) group in them [7]. Amino acids, when added as impurities, have improved material properties [8]. Amino acid, L-Leucine has formed several complexes, which are promising materials for second harmonic generation [9-10]. In the light of research work being done on ADP crystals, to improve the properties, it was thought interesting and worthwhile to investigate the effect of L-Leucine on ADP. In this work, the structural spectral and nonlinear optical behavior of single crystals of L-Leucine added ADP against pure ADP has been studied and reported.



**Fig.1:** Pure ADP and 0.8 % L-Leucine doped crystal.

## 2. Experiment



Ammonium dihydrogen phosphate and L-leucine (Merck-Germany) along with de-ionised water were used for the growth of single crystals. ADP was mixed with L-leucine in the ratio 1:0.08 to prepare 200 ml of saturated solution at 38°C and 100 ml of saturated solution of pure ADP was also prepared with de-ionised water at 35°C. The solution was stirred for four hours using magnetic stirrer[29]. It was then filtered using Whatmann filter paper, transferred to borosil glass beaker, porously sealed and kept in a dust free atmosphere for slow evaporation. The grown Pure and 0.8 mol% L-leucine added ADP crystals were harvested after a period of 30 days. Crystals growth and characterization of

ADP and doped ADP crystals were grown from an aqueous solution by slow evaporation and slow cooking techniques. Good quality crystals of reasonable size (40 mm X8 mmX 7 mm) are obtained for a particular concentration shown in fig 1.

## 3. Characterization Analysis

The grown single crystal of ADP was subjected to different characterization studies such as powder X-ray diffraction, FT-IR and Thermal stability of the sample was tested using DTA and thermo gravimetric analysis (TGA).

### 3.1. X-ray Diffraction Analysis:




**Fig. 2:** XRD of Pure ADP Crystal and 0.8% doped ADP with L-Leucine.

XRD studies were carried out with the grown crystals in powdered form. The powder samples were loaded into Bruker AXS D8 Advance X-ray diffractometer with Cu K $\alpha$  radiation ( $\lambda = 1.5417$ ) with an applied operating voltage 40 kV and current 35 mA. Scanning rate was maintained at 18  $\text{min}^{-1}$  over a  $2\theta$  range of 10–80°, employing the reflection mode for scanning. From this measurement we found the lattice dimensions as:  $a = b = 7.4854 \text{ \AA}$ ,  $c = 7.5377 \text{ \AA}$ ,  $\alpha = \beta = \gamma = 90^\circ$  having space group  $I42dd$  and the lattice parameters are in good agreement with the reported values. XRD values of ADP crystallites are in good agreement with standard JCPDS card No. 850815. There are no other phases that were observed beside the tetragonal system. The prominent peaks in the XRD pattern have been indexed as shown in Fig2. The differences in the peak amplitude can be attributed to the different sizes and orientation of the powdered grains.

### 3.2. Fourier Transforms Infrared (FT-IR) Analysis:

The Fourier Transform Infra-Red (FTIR) investigations were also carried out on the powdered samples of ADP. The spectrum was observed from Thermo Nicolet, Avatar 370 spectrophotometer in the region 400 to 4000  $\text{cm}^{-1}$  using KBr pellet. The prominent peaks in the FTIR pattern have been indexed as shown in Fig. 2. Many useful observations were observed. The group frequency region was located between 4000  $\text{cm}^{-1}$  to 1300  $\text{cm}^{-1}$  and the fingerprint region 1300 to 630  $\text{cm}^{-1}$ . The intermediate frequency range 2500 to 1540  $\text{cm}^{-1}$  (unsaturated region) contains triple bond frequencies which appear from 2500 to 2000  $\text{cm}^{-1}$  and double bond frequencies from 2000 to 1540  $\text{cm}^{-1}$ . In the region between 1300 to 650  $\text{cm}^{-1}$  there are single bond stretching frequencies and bending vibration of polyatomic systems involving motions of bonds linking a substituent group to the molecule



**Fig.3:** FTIR of 0.8% doped ADP with L-Leucine.

In the spectrum of ADP, there is a broadband in the higher energy region due to O–H stretching vibration of ADP and water. Hydrogen bonding within the crystal is suggested to be the cause for broadening. Presence of water is supported by its bending vibrations occurring at the band 1737.05cm<sup>-1</sup> [27]. The bands below 1300cm<sup>-1</sup> is due to PO<sub>4</sub> vibrations. It includes the OH stretch of hydrogen bonded carboxyl groups, the asymmetric stretching mode of NH<sub>3</sub><sup>+</sup> at


3253.71 cm<sup>-1</sup> and CH<sub>2</sub> stretching mode just below 3000 cm<sup>-1</sup>. The absorption at 1737.05 cm<sup>-1</sup> is assigned to C = O stretching of –COOH group. The NH<sub>3</sub><sup>+</sup> displays its characteristic bending modes at 1446.67 cm<sup>-1</sup>. The strong absorption in the range 1100.50 – 912.16 cm<sup>-1</sup> is evidently due to the phosphate part of the molecule. The peaks observed at 547.74 cm<sup>-1</sup> is due to NH<sub>3</sub><sup>+</sup> oscillation [28].

**Table No.1:** Bond assignments of various frequency.

Sr.no	Frequency Range	0.8mole%+ADP	Bond Assignments
1	3700-3100	3253.71	O-H Stretching
2	2800-2300	2409.81	Vibration of combination bond
3	2000-1500	1737.05	Bending vibration of NH <sub>2</sub>
4	1500-1000	1446.67	P-O-H vibration
5	1500-1000	1267.13	P-O-H vibration
6	1500-1000	1100.50	P-O-H vibration
7	1000-700	912.16	P-O-H vibration
8	700-500	547.74	PO <sub>4</sub> Vibration

Crystal	a (A°)	b (A°)	c (A°)	Volume (A <sup>3</sup> )	α=β=γ	System
Ammonium dihydrogen Phosphate (ADP)	7.5006	7.5006	7.5490	425.8	90°	Tetragonal


**3.4. Thermo Gravimetric Analysis (TGA):**



**Fig.4:** TGA of 0.8% L-Leucine doped ADP

Thermo gravimetric and differential thermal analyses give information regarding phase transition, water of crystallization and different stages of decomposition of the crystal system. The thermo gravimetric analysis of MAP single crystal was carried out between 30 °C and 300 °C in the nitrogen atmosphere at a heating rate of 20 °C min<sup>-1</sup> using Perkin Elmer, Diamond TG/DTA analyzer. The thermo gram and the differential thermo gravimetric trace of USA are shown in Fig.3. In the first step of the TGA curve, there is negligible weight is lost within the temperature range from 25°C to 180°C, which indicates that there is no inclusion of water in the crystal lattice, which was used as the solvent for crystallization. The second step of the TGA curve shows about 8 wt.% loss at 180°C to 570°C; that is considered as the de-bonding of bonded H<sub>2</sub>O and the elimination of organic compounds through oxidation.

It seen that the major weight loss starts at 700°C and it continue up to 1020°C. The nature of weight loss indicates the decomposition point of the material. However, above this temp no temperature, no weight loss has been observed. In the DTA the strong endothermic peaks located ~199.20°C depict the crystallization of the phase of decomposed material.



**Fig.5:** EDAX Characterization of 0.8% L-Leucine doped ADP.

#### 4. Conclusion

Optical quality, colorless and pure and 0.4 mole%, L-Leucine doped ADP crystals were grown by slow evaporation technique at room temperature. The powder X-ray diffraction studies of pure and L-Leucine doped ADP showed that crystal possess tetragonal structure having I4<sub>2</sub>d symmetry space group, with lattice parameter in good agreement with JCPDS data card no. 850815. Even after doping crystal system remains unchanged. Intensity peaks of L-Leucine doped ADP crystal resembles with diffraction angle of pure ADP crystal with negligible small variation, while intensity variation observed. The FT-IR spectrum confirms the presence of all functional group of L-Leucine. TGA analysis reveals the different stages of decomposition. The thermal stability of doped crystal is found to be improved.

#### Acknowledgement

Author would like to thank the Principal, Bhawabhuti Mahavidyalaya Amgaon. Also express our gratitude towards Dr. P.S. Sawadh, Dr. K. G. Rewatkar and UGC for funding and providing necessary support and help, also

#### 3.5 EDAX characterization

The composition of the synthesized samples was determined using the energy dispersive X-ray spectroscopy (EDX) analysis. The EDX analysis of L-leucine substituted ADP samples clearly shows that the stoichiometric C, P, N and O content increased. Figure 5 Shows few representative EDX spectra of synthesized L-leucine doped ADP. EDX of samples record all peaks associated to elements of crystal-like carbon, phosphorus, nitrogen and oxygen shown in Fig.5. The chemical composition quantification for L-leucine 0.8%, is presented in Table. It is noticed that doped samples do not generally show any large variations in the contents of all the metal ions from spot to spot on the sample surface suggesting regular surface and intrinsic homogeneity in the samples.

The energy of the consequent radiation emitted from the specimen is related to the atomic number of the elements present in the sample. The EDAX spectrum is a relation between intensity and binding energy of the emitted photoelectron. It is interesting to note that the peak height and area of the peaks are measures of the quantity of the elements incorporated in the specimen.

thankful to the Department of Nanoscience and Nanotechnology Dr. Ambedkar College Nagpur for providing in the nano material synthesis.

#### References

1. Ram Kripal, Santwana Shukla, Prashant Dwivedi, *Physica B* 407 (2012) 656-663.
2. P. Rajesh, K. Boopathi, P. Ramasamy, *J Crystal Growth* 318 (2011) 751-756.
3. K. Srinivasan, A. Cantoni, G. Bocelli, *Cryst. Res. Technol.* 45(7) (2010) 737-746.
4. R. Ananda Kumari, *Ind. J. Pure & Appl. Phys.* 47 (2009) 369-371.
5. Y. Asakuma, Q. Li, H. M. Ang, M. Tade, K. Maeda, K. Fukui, *Appl. Surface Sci.* 254(15) (2008) 4524-4530.
6. Xiue Ren, Dongli Xu, Dongfeng Xue, *J Crystal Growth* 310 (2008) 2005-2009.
7. N. Zaitseva, L. Carman, *Prog. Cryst. Growth Charact.* 43,1 (2001).
8. L. Glasser, *Chem. Rev.* 75,21 (1975).
9. M.J. Gunning, R.E. Raab, W. Kucharczyk, *J. Opt. Soc. Am. B* 18,1092 (2001).

10. E. Rushton, Br. J. Appl. Phys. 12:417 (1961).
11. N. Peres, A. Boukhris, M. Souhassou, G. Gavaille, C. Lecomte, Acta Cryst. A55,1038 (1999).
12. R. Ledzion, K. Bondarczuk, W. Kucharczyk, Cryst. Res. Technol. 39, 161 (2004).
13. [Glass, A.M. and M.E. Lines, Oxford University Press, Oxford, pp 293, (1977).
14. Courtens.E, Helv. Phys. Acta., 56:705 (1983).
15. Ermerl, D. Ferroelectrics, 72:95 (1987).
16. Zaitseva, N.P., L.N.Rashkovich and S.V. Bogatyreva, J. Crystal growth, 148:-276, (1995).
17. Dmitriev, V.G., G.G.Gurzadyan and D.N. Nikogosyan,, Springer – verlag, Berlin, Heidelberg, pp : 14 -35, (1991).
18. A. Jayarama , S.M. Dharmaparakash,” Applied Surface Science 253, 944–949 (2006).
19. A. Claude, V.Vaithianathan, R. Barivava Ganesh, R. Sathiyalakshmi and P.Ramasamy, Journal of Applied Sciences 6 (1): 85 – 89, (2006).
20. A. Abdel-Kader, J. Mater. Sci. - Mater. Electron. 2, 7 (1991).
21. N. Pe`ere`sy,M. Souhassouyx, B.Wynckey, G. Avoilleyx, A. Coussonzand, J. Phys: Condens. Matter 9, 6555 (1997).
22. [16] R. Reintjes, E.C. Eckardt, Appl. Phys. Lett. 30, 91 (1977).
23. R.J. Davey, J.W. Mullin, J. Cryst. Growth 26 ,45 (1974).
24. R.I. Ristic, J.N. Sherwood, J. Phys. D: Appl. Phys. 24, 171 (1991).
25. J. Fontcuberta, R. Rodriguez, J. Tejada, J. Cryst. Growth 44, 593 (1978).
26. A. Boujhris, M. Souhassou, C. Lecomte, B. Wyneke, A. Thalal, J. Phys: Condens. Matter 10, 1621 (1998).
27. C.N. Banwell, E.M. McCash, fourth ed., McGraw-Hill, NewYork, (1994).
28. T. Balu, T.R. Rajasekaran, P. Murugakoothan, Current Applied Physics 9 435–440 (2009).
29. S.Goma, C.M.Padma, C.K.Mahadevan. Elsevier Material latter – 60 (2006) 3701-3705